

tine 28, please delete "liquid carrier" and insert of the

overall decorative enhancement composition

IN THE CLAIMS:

Please cancel Claims 3-4, 6, 9-14, 18-19, and 21-38 without prejudice.

Please amend the claims as follows:

1	1. (Amended) A method for permanent decorative enhancement of a
2	polyethylene surface of a [preformed] molded polyethylene article which comprises

- (a) <u>incorporating</u> [applying] a decorative enhancement composition to said <u>polyethylene</u> surface wherein said decorative enhancement composition consists essentially of:
 - (1) a [20 to 90 weight percent] liquid carrier in an amount

 sufficient to provide the decorative enhancement

 composition with a consistency and viscosity necessary

 for application by liquid methods of application; and
 - (2) <u>a first</u> [10 to 80 weight percent] mixture consisting essentially of:
 - (A) <u>a</u> [9 to 50 weight percent] colorant <u>in an amount</u>
 sufficient to impart a desired surface color; and
 - (B) [50 to 91 weight percent of] a second mixture consisting essentially of.
 - (i) [30 to 70 weight percent of] a binder [solid] in an amount

3

13

14

15

16



sufficient to provide adhesion of the decorative
enhancement composition to said polyethyl ne
surface [selected from the group consisting of
hydrocarbon resins, petroleum, synthetic and
emulsifiable waxes, rosins, rosin-esters, terpene
based resins, and chlorinated polyelefin resins]; and
(ii) a [70 to 30 weight percent] particulate thermoplastic

powder in an amount sufficient to fuse into and form a permanent bond with the molded

polyethylene article [selected from the group consisting of polyethelene, polypropylene, and ethylene vinyl acetate co-polymers wherein said powder has a density from 0.88 to 0.97 and a particle size no greater than 140 microns diameter]; and

(b) heating said [deposited] decorative enhancement composition and said [interfacing surface] molded polyethylene article to produce a molded polyethylene article having [to an elevated temperature and time sufficient to fuse said decorative enhancement composition to said surface to form a permanent] a permanently colored decoratively enhanced surface [of the preformed article] characterized by said colorant on and in said polyethylene surface of said molded poly thylene article

2. (Amended) The method of Claim [4] 39 wherein said liquid carrier comprises 60 to 90 weight percent of said decorative enhancement composition for use in applying said decorative enhancement composition by spray methods.

5. (Amended) The method of Claim 1 wherein said colorant is an organic pigment from the [groups] group consisting of pthalocyanines, carbazole dioxanines, monoazo-based, diazo based, and quinacridones 15. (Amended) The method of Claim 1 further including application of a clear overcoat composition to [the] an exposed surface of said permanent decoratively enhanced surface.

17. (Amended) The method of Claim 16 further including the fusing of said overcoat to said permanently colored **decoratively** enhanced surface the application of a temperature greater than 250 degrees Fahrenheit without overheating to cause warpage.

Please add the following new claims:

1

4

1

39. The method of Claim wherein said molded polyethylene article is a preformed molded polyethylene article.

40. The method of Claim 39 wherein said incorporating step is accomplished by applying said decorative enhancement composition to said preformed molded polyethylene article.

1

2

3

1

2

3

- 41. The method of Claim 40 wherein said heating step is accomplished
 by heating said decorative enhancement composition and said preformed molded
 polyethylene article to a temperature and for a time sufficient to fuse said decorative
 enhancement composition to said preformed molded polyethylene article.
 - 42. The method of Claim 1 wherein said liquid carrier comprises 20 to 90 weight percent of said decorative enhancement composition.
- 43. The method of Claim 1 wherein said first mixture of said colorant, said binder, and said particulate thermoplastic pewder collectively comprise 10 to 80 weight percent of said decorative enhancement composition.
 - 44. The method of Claim 45 wherein said colorant comprises 9 to 50 weight percent of said first mixture and said binder and said particulate thermoplastic powder collectively comprises 50 to 91 weight percent of said first mixture.
- 45. The method of Claim 44 wherein said binder comprises 30 to 70 weight percent of said second mixture and is selected from the group consisting of hydrocarbon resins, petroleum, synthetic waxes, emulsifiable waxes, rosins, rosinesters, terpene based resins, and chlorinated polyolefin resins.

46. The method of Claim 44 wherein said particulate thermoplastic

2 powder comprises 70 to 30 weight percent of said second mixture and is selected from

the group consisting of polyethere, polypropylene, and ethylene-vinyl acetate co-

polymers wherein said powder has a density from 0.88 to 0.97 and a particle size no

greater than 140 microns diameter

1